



33948

20/03/2014

EIGENSCHAFTEN

- ACS : 19ACCLY406

ZERTIFIZIERUNGEN



TECHNISCHE DATEN

- Recommandé : 3 bars (max. 5 bars) - Advised : 43,5 psi (max. 72 psi)
- 9,5 l/min à 3 bars (2.5 gpm at 43.5 psi)

VERFÜGBARE OBERFLÄCHEN

- Chrom - A02
- Chrom / gold - G02
- Gold - F01
- Nickel matt - C01
- Silbernickel - B01